

ZG-90 ANTI-RUST PAINT COLOURS



MARKET SECTORS:

INDUSTRIAL MRO
FASTENERS & FIXINGS
ELECTRICAL MRO
AGRICULTURE
TRADE/PRO-DIY

CODE	FILL SIZE/PRODUCT
1935	500ml aerosol / Black (RAL 9005)
1936	500ml aerosol / White (RAL 9010)
1937	500ml aerosol / Green (RAL 6010)
1938	500ml aerosol / Red (RAL 3000)
1939	500ml aerosol / Blue (RAL 5012)
2045	500ml aerosol / Yellow (RAL 1004)

ZG-90 zinc phosphate enhanced paints which prime and top-coat in one application. Provides a superior combination of good drying time, great coverage & solid opacity. Demonstrates superior corrosion protection (meets ISO 12944-2, cat. C3, tested to ASTM B117) and adhesion (tested to ISO 2409:0). The paints are RAL matched for accurate and consistent colour reproduction with a long-lasting satin finish.

KEY FEATURES

- Effective protection against corrosion
- Excellent adhesion and flexibility for long-term performance (ISO 2409:0)
- Tested to ASTM B117 and DIN EN ISO 12944-2

APPLICATION AREAS

General fabrication: Use on bare, degreased metal to provide an effective, colour-matched finish with good long-term protection.

Facility Maintenance: use for repairing and maintaining fences, metal sheets, air conditioning units and ducting.

Complementary products: TF-90 for surface degreasing, MZ-90 for a 2-layer anticorrosion system, for Cathodic protection.
 TF-90 / Partcode 1848
 MZ-90 / Parcode 1972

COLOUR REFERENCES

BLACK	RAL 9005	Non-flammable liquids
WHITE	RAL 9010	General use
GREEN	RAL 6010	Water
RED	RAL 3000	Fire Fighting
BLUE	RAL 5012	Air
YELLOW	RAL 1004	Gas and liquified gas

- Also available as ZG-90 Silver - see separate data sheet / Partcode 1785

DIRECTIONS FOR USE

- Use in well ventilated area.
- Ensure that the surface to be coated is clean, dry and free from grease. Remove any rust and scale with a wire brush.
- ZG-90 contains solids which settle during storage: shake the can vigorously until the agitator ball is free and continue shaking for a further minute.
- Shake the can periodically during application.
- Apply in light, even coats - best results are obtained with 2 light coats rather than one heavy coat.
- Additional coats can be applied after 15 - 20 minutes. When spraying is finished, clean the aerosol valve by turning the can upside down and spray until only propellant escapes.
- Do no use on the inside of water storage tanks.

APPEARANCE:	Matched to RAL colour
ODOUR:	Solvent
FILM THICKNESS PER COAT:	30 µm
TOUCH DRY:	20 minutes
FULL CURED:	6 hours
MAXIMUM TEMPERATURE RESISTANCE OF CURED FILM:	80°C
MINIMUM APPLICATION TEMPERATURE (SUBSTRATE):	10°C
SALT SPRAY RESISTANCE (ISO 12944, CATEGORY C3):	>220 hours

(All values apply to product without aerosol propellant)

HEALTH AND SAFETY

A separate Safety Data Sheet (SDS) is available from <https://www.actioncan.com/product/zg-90/> or from info@actioncan.com

STORAGE & SHELF LIFE

The product may be stored at normal ambient temperatures and has a shelf life of not less than 72 months with correct storage. Aerosols should always be stored below 50°C, away from direct heat and naked flame.

MISREPRESENTATION ACT 1967 & TRADE DESCRIPTIONS ACT 1968

The information given in this publication is based on our experience and reports from customers. There are many factors outside our control and knowledge which affect the use and performance of our products and for which reason no warranty is given, express or implied. Users should make their own tests to determine the applicability of such information or the suitability of any products for their own particular purposes. Statements concerning the use of the products described herein are not to be construed as recommending the infringement of any patent and no liability for infringement arising out of any such use is to be assumed.

TECHNICAL SERVICE

CRC Industries UK Ltd provides a technical support service and maintains a constant programme of research and development. Should you have a technically complex enquiry, please email us for specialist/laboratory support.

